

PRODUCT CERTIFICATE

Finished Product Laboratory

ISO 13006-10545

Equivalent to the Brazilian Norm NBR 13818

Dry-pressed ceramic tiles Eb > 10% Group BIII

PRODUCT: GAP NUDE 30X60 Glossy
Rectified

TIPOLOGY: Wall

SIZE: 30X60

CODE: 27164E

LINE: AZULEJA



Characteristics	Test as per	Results
Physical		
Water Absorption (%E)	ISO 10545-3 NBR 13818 - annex: B (Eb > 10%)	>10
Modulus of Breaking Strength (MPa)	ISO 10545-4 NBR 13818 - annex: C (Average: ≥ 15)	15
Breaking Load (N)	ISO 10545-4 NBR 13818 - annex: C (Average: ≥ 600)	600
Moisture Expansion (mm/m)	ISO 10545-10 NBR 13818 - annex: J	0,4
Crazing Resistance	ISO 10545-11 NBR 13818 - annex: F	Resist
Frost Resistance	ISO 10545-12 NBR 13818 - annex: M	NA
Resistance to Thermal Shock	ISO 10545-9 NBR 13818 - annex: L	Not Resist
Chemical		
Resistance to Stains		
Green staining agent in light oil		5
Red staining agent in light oil		5
Iodine	ISO 10545-14 NBR 13818 - annex: G (Minimum: 3)	5
Olive Oil		5
Chemical Resistance		
Hydrochloric Acid 3% (v/v)		A
Potassium Hydroxide 30g/L		A
Citric Acid 100g/L		A
Lactic Acid 5% (v/v)	ISO 10545-13 NBR 13818 - annex: H (Minimum: B)	A
Hydrochloric Acid 18% (v/v)		A
Potassium Hydroxide 100g/L		A
Ammonium Chloride 100g/L		A
Sodium Hypochloride 20mg/L		A

Coefficient of Friction		
Dry Surface	NBR 13818 - annex: N Method: TORTUS III (Value \geq 0,4)	NA
Wet Surface		NA
Wet Surface	ANSI A137. Section 9.6 (Minimum Average Value 0,42)	NA

Local of Use

IC - Internal Coating

Recommendation for Application

For information on application recommendations, refer to the virtual specifier: <http://especificadorvirtual.portobello.com.br>
Tijucas, 07/12/2020

Portobello



eb58ee25999160c184750a6615ba5825d9906373

Portobello SA - Factory | contato@portobello.com.br | SAC: 800 648 2002 | BR 101 - Km 163 - PO Box 15 - Tijucas/SC - Brazil - 88200-000